NC2SW.015 0.2OZ

Datasheet revision 1.3 www.chipquik.com

Solder Wire Sn60/Pb40 No-Clean with 2.2% Flux Core 0.2oz Tube

Product Highlights

No-Clean Synthetic Flux Core

The clear, non-corrosive, non-conductive residue is meant to be left on the board.

2.2% flux core

Halogen content: None

Specifications

Alloy: Sn60/Pb40
Wire Diameter: 0.015" (0.38mm)
Flux Type: No-Clean Synthetic

Flux Classification: ROL0

Melting Point: 183-188°C (361-370°F)

Packaging: 0.2 oz Tube Shelf Life: >60 months



Test Results

| I CSL NCSUILS | | |
|--|---|--|
| Test J-STD-004 or other requirements as stated | Test Requirement | Result |
| • | IDO TM 050, 0 0 00 | I. No bus alethus cub |
| Copper Mirror | IPC-TM-650: 2.3.32 | L: No breakthrough |
| Corrosion | IPC-TM-650: 2.6.15 | L: No corrosion |
| Quantitative Halides | IPC-TM-650: 2.3.28.1 | L: <0.05% |
| Electrochemical Migration | IPC-TM-650: 2.6.14.1 | L: <1 decade drop (No-clean) |
| Surface Insulation Resistance 85°C, | IPC-TM-650: 2.6.3.7 | L: ≥100MΩ (No-clean) |
| 85% RH @ 168 Hours | | , |
| Visual | IPC-TM-650: 3.4.2.5 | Clear and free from precipitation |
| Conflict Minerals Compliance | Electronic Industry Citizenship Coalition (EICC) | Compliant |
| REACH Compliance | Articles 33 and 67 of Regulation (EC) No 1907/2006 | Contains Lead (Pb) CAS# 7439-92-1 No other SVHC present |

Conforms to the following Industry Standards:

J-STD-004B, Amendment 1 (Solder Fluxes):

Yes
J-STD-006C, Amendments 1 & 2 (Solder Alloys and Fluxed/Non-Fluxed Solders):

Yes

RoHS 3 Directive (EU) 2015/863: