

Datasheet revision 1.3

www.chipquik.com

## Solder Wire SAC305 No-Clean with 2.2% Flux Core 1lb Spool

Product Highlights No-Clean Synthetic Flux Core The clear, non-corrosive, non-conductive residue is meant to be left on the board. 2.2% flux core Halogen content: None RoHS 3 and REACH compliant

| Sn96.5/Ag3.0/Cu0.5    |
|-----------------------|
| 0.020" (0.5mm)        |
| No-Clean Synthetic    |
| ROL0                  |
| 217-220°C (423-428°F) |
| 1 lb spool            |
| >60 months            |
|                       |

## **Test Results**

| Test J-STD-004 or other requirements as stated            | Test Requirement                                      | Result   |
|---|---|--|
| Copper Mirror   | IPC-TM-650: 2.3.32                                    | L: No breakthrough   |
| Corrosion   | IPC-TM-650: 2.6.15                                    | L: No corrosion  |
| Quantitative Halides                                      | IPC-TM-650: 2.3.28.1                                  | L: <0.05%  |
| Electrochemical Migration                                 | IPC-TM-650: 2.6.14.1                                  | L: <1 decade drop (No-clean)   |
| Surface Insulation Resistance 85°C,<br>85% RH @ 168 Hours | IPC-TM-650: 2.6.3.7                                   | L: ≥100MΩ (No-clean)   |
| Visual  | IPC-TM-650: 3.4.2.5                                   | Clear and free from precipitation  |
| Conflict Minerals Compliance                              | Electronic Industry Citizenship<br>Coalition (EICC)   | Compliant  |
| REACH Compliance  | Articles 33 and 67 of Regulation (EC)<br>No 1907/2006 | Contains no substance >0.1% w/w that<br>is listed as a SVHC or restricted for<br>use in solder materials |

| Conforms to the following Industry Standards:                               |     |
|---|-----|
| J-STD-004B, Amendment 1 (Solder Fluxes):                                    | Yes |
| J-STD-006C, Amendments 1 & 2 (Solder Alloys and Fluxed/Non-Fluxed Solders): | Yes |
| RoHS 3 Directive (EU) 2015/863:   | Yes |