

Heat Sink Compound - High Density 10g Syringe 5cc

Product Highlights

- High Density Thermal Paste.
- White, non-curing and non-flowing thermally conductive heat sink compound.
- Heavily filled with heat-conductive metal oxide. Provides high thermal conductivity, low bleed and high temperature stability.
- Electrically insulating (2×10^{15} ohm-cm).

Specifications

Viscosity:	542,000 cP (542,000 mPa·s)
Density:	2.1g/cc
Bleed:	0.23%
Thermal Conductivity:	0.67 W/m·K
Thermal Resistance:	0.16 °C*cm ² /W
Electrical Volume Resistivity:	2×10^{15} ohm-cm
Dielectric Strength:	8.27 MV/m (210V/mil)
Evaporation:	0.38%
Size:	10g Syringe (5cc)

Storage and Handling

Store refrigerated or at room temperature 3-25°C (37-77°F). Allow 4 hours for thermal paste to reach an operating temperature of 20-25°C (68-77°F) before use.

Shelf Life

>60 months

Transportation

This product has no shipping restrictions. Shipping below 0°C (32°F) or above 25°C (77°F) for normal transit times by ground or air will not impact this product's stated shelf life.



Chip Quik® Thermal Paste Orderable Part Numbers

Thermal Conductivity (W/m·K)	Thermal Resistance (°C·cm²/W)	Density (g/cc)	Color	Package	Size (g)	Orderable Part Number
0.67	0.16	2.1	White	Syringe	10	TC1-10G
0.67	0.16	2.1	White	Syringe	20	TC1-20G
0.67	0.16	2.1	White	Jar	200	TC1-200G
4.3	0.06	2.5	Grey	Syringe	10	TC2-10G
4.3	0.06	2.5	Grey	Syringe	20	TC2-20G
4.3	0.06	2.5	Grey	Jar	50	TC2-50G